



TECHNICAL DATA SHEET

WALL CHARM LATEX SATIN

104-01

06/23/2008

PRODUCT CHARACTERISTICS

DESCRIPTION		RECOMMENDED USES	
<ul style="list-style-type: none"> A durable, premium quality, satin finish wall paint for interior surfaces. Dries to a soft gloss finish. Excellent washability. Low odor / Low VOC & Fast Dry Available in Hi-Hide base to give one coat coverage in most cases Soap & water cleanup 		<ul style="list-style-type: none"> Recommended for interior drywall, plaster, wood, concrete, and metal that has been properly prepared. Do not mix with oil colors, other paints, or solvents. Not recommended for use on tub or shower stalls, floors or any surface that will be under water. 	
COLORS		FINISH	Satin
104-01 White	104-03 Oyster White	VEHICLE	Acrylic Latex Emulsion
104-91 HHB	104-05 White Pearl	FORMULATION	Lead, chromate, and mercury free
104-92 LTB	104-06 Antique White		
104-93 MTB			
104-94 DTB			
104-95 CTB			

PHYSICAL DATA

GLOSS RATING	15-25%	VISCOSITY	98-100 K.U.
PERCENT SOLIDS	By weight: 49.6 ± 2.0% By volume: 34.6 ± 2.0%	NET WT. PER GAL.	10.9 ± 0.25 lbs./gal.
VOC CATEGORY	1.3 lbs./gal. (150 grams/liter)	FLASH POINT	>200 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New plaster or cement surfaces should age at least 30 days before being painted.
- To maximize holdout and minimize the number of finish coats needed to achieve a uniform appearance, a first coat of the proper primer is recommended. In all cases, bare metal must be primed. Glossy surfaces should be dulled with fine sandpaper and primed with Classic 245 Versa Seal.
- Previously painted surfaces should be cleaned, patched, and spot primed before top coating. Two coats of this product are recommended on most surfaces.

RECOMMENDED PRIMERS		RECOMMENDED APPLICATION	
Drywall	245-88 Classic Versa Seal	Brush:	As supplied
Plaster	245-88 Classic Versa Seal	Roller:	As supplied
Wood	245-88 Classic Versa Seal	Spray:	Up to 10:1 reduction with clean water
Masonry	245-88 Classic Versa Seal	Airless:	As supplied
Metal	622-71,-72,-73 Defi-Rust Acrylic Primers		
Galvanizing	245-88 Classic Versa Seal		
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.		STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.	
TINTING	Hundreds of additional colors may be obtained by using the tint bases and approved colorants.	DRYING TIME	Tack free: 4 hrs.
		(Good Conditions)	To recoat: 8-12 hrs.
			Hard: 48 hrs.
PRACTICAL COVERAGE	400 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION	Not normally recommended. If necessary use small amounts of clean water. (For spray reduction see recommended application)
RECOMMENDED FILM PER COAT	Wet: 3.0-4.0 mils Dry: 1.0-1.4 mils	CLEAN-UP	Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	104-01, 104-91, 104-92, 104-93	5 Gallon	Gallon	Quart
	104-03	5 Gallon	Gallon	Quart
	All Other Bases & Colors		Gallon	Quart
FREIGHT CLASS	Non-Flammable Paint	MSDS	Available upon request.	

HPF-0054, Rev. 1, 8/21/98

Harrison Paint Company • 1329 Harrison Ave SW, Canton, OH 44706
Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750