



TECHNICAL DATA SHEET

Interior

WALL CHARM LATEX SEMI-GLOSS

106-01

06/23/2008

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> • A durable, premium quality, semi-gloss finish wall paint for interior surfaces. Dries to a moderate gloss. Excellent washability. • Low odor / Low VOC & Fast Dry • Available in Hi-Hide base to give one coat coverage in most cases • Soap & water cleanup 	RECOMMENDED USES <ul style="list-style-type: none"> • Recommended for interior drywall, plaster, wood, concrete, and metal that has been properly prepared. • Do not mix with oil colors, other paints, or solvents. • Not recommended for use on tub or shower stalls, floors or any surface that will be under water.
COLORS 106-01 White 106-03 Oyster White 106-91 HHB 106-05 White Pearl 106-92 LTB 106-06 Antique White 106-93 MTB 106-94 DTB 106-95 CTB	FINISH Semi-Gloss VEHICLE Acrylic Latex Emulsion FORMULATION Lead, chromate, and mercury free

PHYSICAL DATA

GLOSS RATING 45-55%	VISCOSITY 98-100 K.U.
PERCENT SOLIDS By weight: 48.0 ± 2.0% By volume: 34.1 ± 2.0%	NET WT. PER GAL. 10.6 ± 0.25 lbs./gal.
VOC CATEGORY 1.3 lbs./gal. (150 grams/liter)	FLASH POINT >200 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New plaster or cement surfaces should age at least 30 days before being painted.
- To maximize holdout and minimize the number of finish coats needed to achieve a uniform appearance, a first coat of the proper primer is recommended. In all cases, bare metal must be primed. Glossy surfaces should be dulled with fine sandpaper and primed with Classic 245 Versa Seal.
- Previously painted surfaces should be cleaned, patched, and spot primed before top coating. Two coats of this product are recommended on most surfaces.

RECOMMENDED PRIMERS Drywall 245-88 Classic Versa Seal Plaster 245-88 Classic Versa Seal Wood 245-88 Classic Versa Seal Masonry 245-88 Classic Versa Seal Metal 622-71,-72, -73 Defi-Rust Acrylic Primers Galvanizing 245-88 Classic Versa Seal	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING Hundreds of additional colors may be obtained by using the tint bases and approved colorants.	DRYING TIME (Good Conditions) Tack free: 4 hrs. To recoat: 8-12 hrs. Hard: 48 hrs.
PRACTICAL COVERAGE 400 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION Not normally recommended. If necessary use small amounts of clean water. (For spray reduction see recommended application)
RECOMMENDED FILM PER COAT Wet: 3.0-4.0 mils Dry: 1.0-1.4 mils	CLEAN-UP Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	106-01, 106-91, 106-92 All Other Bases & Colors	5 Gallon Gallon Quart Gallon Quart
FREIGHT CLASS	Non-Flammable Paint	MSDS Available upon request.

HPF-0054, Rev. 1, 8/21/98

Harrison Paint Company • 1329 Harrison Ave SW, Canton, OH 44706
 Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750