

Interior/Exterior

## VERSA-SEAL "CLASSIC 245" ACRYLIC PRIMER

245-88

8/15/14

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A fast drying, waterborne, multi-purpose, primer/sealer formulated for exceptional adhesion to a variety of surfaces.</li> <li>• Outstanding hide helps cover previous coatings and color variations.</li> <li>• Seals out smoke damage from fires and asphalt stains.</li> <li>• Exhibits good holdout and minimal grain raising properties.</li> <li>• Soap and water cleanup.</li> <li>• Low odor / low VOC formulation (compliant for most areas).</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• May be used on bare or previously coated drywall, plaster, wood, masonry, and primed ferrous metal surfaces.</li> <li>• Adheres to most flat to glossy old paint, paneling, aluminum and vinyl siding, galvanized metal, and many other clean, sound, substrates.</li> <li>• May be used as a primer under wallpaper.</li> <li>• Not intended to be used as a finish coat.</li> </ul>
<b>COLORS</b> 245-88 White	<b>FINISH</b> Flat (Slight Sheen) <b>VEHICLE</b> Acrylic Polymers <b>FORMULATION</b> Formulated without lead, chrome, and mercury

### PHYSICAL DATA

<b>GLOSS RATING</b> Less than 5%	<b>VISCOSITY</b> 96-100 KU
<b>PERCENT SOLIDS</b> Weight: 53% +/- 2.0 Volume: 34% +/- 2.0	<b>NET WT. PER GAL.</b> 11.6 +/- 0.25 lbs./gal.
<b>VOC CATEGORY</b> Less than 150 grams/liter	<b>FLASH POINT</b> Higher than 200°F

### SURFACE PREPARATION & APPLICATION INSTRUCTIONS

- Read label directions for detailed instructions. Correct for the cause of any previous paint failures before applying this product.
- New plaster and masonry should age at least 30 days before being primed.
- Joint compound must be completely dry and smooth before priming.
- A stain blocking primer/sealer is recommended on woods containing bleeding extractives (tannins) and over most stains other than smoke damage from fires and asphalt.
- Although this product exhibits excellent adhesion to many surfaces, scuff sanding smooth, hard, and/or glossy surfaces is recommended to optimize adhesion.
- Note: This product will continue to cure, harden, and gain adhesion for up to 30 days after application under good conditions.

#### RECOMMENDED PRIMERS

Drywall/Plaster:	None
Masonry:	None
Wood:	None or 248-88 Versa-Seal Acrylic Stain Block
Ferrous Metal:	622-71, 72, 73 Defi-Rust Acrylic Metal Primer
Galvanized:	None

#### RECOMMENDED APPLICATION

Brush:	As supplied
Roller:	As supplied
Spray:	As supplied
Airless:	As supplied

<b>APPLICATION TEMP.</b> Minimum: 50°F Maximum: 90°F	<b>STORAGE TEMP.</b> Minimum: 50°F Maximum: 90°F
--	--

<b>TINTING</b> Up to 4 fluid ounces per gallon with approved colorants. The addition of colorant may extend drying times.	<b>DRYING TIME (Good Conditions)</b> <table border="0"> <tr> <td>Tack Free:</td> <td>30 min.</td> </tr> <tr> <td>To Topcoat:</td> <td>1 hr.</td> </tr> <tr> <td>Hard:</td> <td>18-24 hrs.</td> </tr> </table>	Tack Free:	30 min.	To Topcoat:	1 hr.	Hard:	18-24 hrs.
Tack Free:	30 min.						
To Topcoat:	1 hr.						
Hard:	18-24 hrs.						

<b>PRACTICAL COVERAGE</b> 300-400 sq. ft. per gallon (Depends on substrate texture and porosity)	<b>REDUCTION</b> Apply without thinning (Use small amounts of clean water only if necessary).
--	---

<b>RECOMMENDED FILM PER COAT</b> <table border="0"> <tr> <td>Wet:</td> <td>4.0-5.3 mils</td> </tr> <tr> <td>Dry:</td> <td>1.4-1.8 mils</td> </tr> </table>	Wet:	4.0-5.3 mils	Dry:	1.4-1.8 mils	<b>CLEANUP</b> Soap and water
Wet:	4.0-5.3 mils				
Dry:	1.4-1.8 mils				

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b> <table border="0"> <tr> <td>245-88</td> <td>White</td> </tr> <tr> <td>245-94</td> <td>DTB</td> </tr> </table>	245-88	White	245-94	DTB	<table border="0"> <tr> <td>5 Gallon</td> <td>1 Gallon</td> <td>1 Quart</td> </tr> <tr> <td></td> <td>1 Gallon</td> <td>1 Quart</td> </tr> </table>	5 Gallon	1 Gallon	1 Quart		1 Gallon	1 Quart
245-88	White										
245-94	DTB										
5 Gallon	1 Gallon	1 Quart									
	1 Gallon	1 Quart									

<b>FREIGHT CLASS</b> Not Regulated	<b>MSDS</b> Available upon request
------------------------------------	------------------------------------