

Exterior

## WONDER FLOW ACRYLIC LATEX SATIN HOUSE PAINT

124-01

8/19/14

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>A waterborne paint formulated with the highest quality ingredients to form a long-lasting protective and decorative finish for exterior surfaces.</li> <li>Flexible and breathable coating resists cracking, peeling, and blistering.</li> <li>Dried film is chalk, fade, weather, and mildew resistant.</li> <li>Soap and water cleanup.</li> <li>Low VOC formulation (compliant for most areas).</li> </ul>			<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>Designed for painting exterior wood siding, shakes, shingles, trim, plywood, shutters, and other wood surfaces.</li> <li>Also designed for application to stucco, cement block, brick, poured in-place and precast concrete, and other masonry substrates.</li> <li>Great for aluminum and vinyl siding and for primed metal.</li> <li>Ideal for houses, barns, gazebos, fences, commercial buildings, and many other structures.</li> <li>Not for use on horizontal surfaces where water collects.</li> </ul>		
<b>COLORS</b> 124-19 Cordovan 120-93 MTB	124-01 White 124-26 Adobe Red 124-94 DTB	124-02 Black 124-92 LTB 124-95 CTB	<b>FINISH</b> Satin	<b>VEHICLE</b> Acrylic Polymer	
			<b>FORMULATION</b> Formulated without lead, chrome and mercury		

### PHYSICAL DATA

<b>GLOSS RATING</b> 20-30%	<b>PERCENT SOLIDS</b> Weight: Varies (46% ± 2.0 is typical) Volume: 33% ± 2.0	<b>VISCOSITY</b> 96-100 KU	<b>NET WT/GAL</b> Varies (10.0 ± 0.25 lbs./gal. is typical)
<b>VOC CATEGORY</b> Less than 150 grams/liter	<b>FLASH POINT</b> Higher than 200°F (Setaflash)		

### SURFACE PREPARATION & APPLICATION INSTRUCTIONS

- Read label directions for detailed instructions.
- Correct for the cause of any previous paint failures before applying this product.
- New masonry should age at least 30 days before being painted.
- For best results on bare wood, first prime with Versa-Seal Exterior Acrylic or Oil Base Wood Primer (follow label instructions).
- Satisfactory results may also be achieved by applying directly on properly prepared bare wood.
- This product is not designed to stop wood bleed (tannin stains). Use of a Versa-Seal Exterior Wood Primer is recommended.
- May be applied directly on properly prepared bare masonry.
- Bare metal must first be primed with a Defi-Rust Acrylic Metal Primer before applying this product (follow label instructions).

<b>RECOMMENDED PRIMERS</b> Wood: 250-77 or 251-77 Versa-Seal Wood Primers Metal: 622-71, 72, 73 Defi-Rust Acrylic Metal Primers Galvanizing: 622-71, 72, 73 Defi-Rust Acrylic Metal Primers Masonry: Direct Application Aluminum Siding: Direct Application Vinyl Siding: Direct Application	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
<b>APPLICATION TEMP.</b> Minimum: 38°F    Maximum: 90°F	<b>STORAGE TEMP.</b> Minimum: 60°F    Maximum: 80°F
<b>TINTING</b> Hundreds of colors may be obtained using the tint bases with approved colorants.	<b>DRYING TIME (Good Conditions)</b> Tack Free: 2 hrs. To Recoat: 12 hrs. Hard: 48 hrs.
<b>PRACTICAL COVERAGE</b> 400 sq. ft./gal. (Depends on substrate texture and porosity)	<b>REDUCTION</b> Apply without thinning (Use small amounts of clean water only if necessary)
<b>RECOMMENDED FILM PER COAT</b> Wet: 3.8-4.2 mils Dry: 1.3-1.4 mils	<b>CLEANUP</b> Soap and water

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b> 124-01    124-92    124-93 124-94    124-95 Standard Colors	5 Gallon    1 Gallon    1 Quart 1 Gallon    1 Gallon    1 Quart 1 Gallon    1 Gallon    1 Quart
<b>FREIGHT CLASS</b> Not regulated	<b>MSDS</b> Available upon request