

Technical Data Sheet

Product #: 196-4305 – Clear High Gloss

Product Name: 2K Waterborne Graffiti Control Coating

Description: A zero VOC, zero HAPs, low odor, catalyzed aliphatic polyurethane coating that provides a permanent film allowing easy graffiti removal while protecting the substrate. This product exhibits outstanding hardness and adhesion and provides excellent abrasion, chemical, solvent, and UV resistance. This high gloss, clear finish is designed for use on properly prepared bare or previously painted masonry, wood, and metal surfaces.

Properties:

Physical:	Application:
Color: Clear	Viscosity: As is
Weight/Gallon: 8.8 +/- 0.25 lbs./gal. (mixed)	Reduction: Apply without thinning
Viscosity: 85-90 KU (mixed)	Reducer: N/A
Gloss: >90%	Application Method: Brush/Roll/Spray
Weight Solids: 55% +/- 2.0 (mixed)	Cleanup: Soap & water
VOC (theoretical): Zero (for mixture)	Coverage (sq.ft./gallon): 325-500/coat (2 coats required)
Pot Life: 1-2 hours @ 77°F	Wet Film Thickness: 3.0-5.0 mils/coat
Mix Ratio: (by Volume) 2:1 (A:B)	Dry to Recoat: 4-6 hours (ideally) ≤12 hours (required)
Mixing Time: 2-3 minutes	Dry Hard: 48 hours
Induction Time: None	Full Cure: 5 days
Flash Point: > 200°F	Note: Drying times are at 70°F and 58% RH. Cool temperatures, high humidity, poor ventilation or heavy film thicknesses will extend dry times. Warmer temperatures and lower humidity will decrease dry times.
Storage: 1 year unopened at 77°F	

Notes:	<p>Mix Part A thoroughly then add the full contents of Part B to Part A and blend completely (2-3 minutes). A drill mounted impeller is recommended for best mixing. Apply when air and surface temperatures are 50-90°F and the relative humidity is less than 85%. Do not apply if rain is expected within 48 hours of application. A minimum of two coats are required at the recommended spreading rate. Do not exceed the spreading rate as this may cause pinholes, micro-blistering, or a milky appearance. If over 12 hours lapses between coats, lightly scuff sand the surface and remove all dust before applying the next coat. For proper performance, the finish must be a uniform, continuous film with no pinholes or other defects. Contact Harrison Paint for approved graffiti remover.</p>
---------------	--

The information and data given herein are based upon tests and reports considered reliable and believed to be accurate. However, due to circumstances beyond our control including but not limited to surface preparation, application technique, substrate and curing conditions, no guarantee of duplicate performance, expressed or implied, is made.