

Technical Data Sheet

Product #: 196-4524 – Clear High Gloss

Product Name: EZ Clean - Waterborne Dry Erase Coating

Description: A zero VOC, zero HAPs, low odor, clear gloss, waterborne catalyzed urethane. When applied over Dutch Standard Tintable Dry Erase Basecoat, it converts interior or exterior smooth surfaces into a dry erase surface in the color of your choice. Dry Erase Basecoat may be applied to drywall, plaster, wood, masonry, aluminum and galvanized metal.

Properties:

Physical:		Application:	
Color:	Clear	Viscosity:	As is
Weight/Gallon:	9.0 +/- 0.25 lbs./gal. (mixed)	Reduction:	≤ 8 fl oz per gallon for spraying
Viscosity:	80-85 KU (mixed)	Reducer:	Water
Gloss:	>90%	Clean Up:	Soap and water
Weight Solids:	54% +/- 2.0 (mixed)	Application Method:	Brush/Roll/Spray
Volume Solids:	47% +/- 2.0 (mixed)	Wet Film Thickness:	3.0-5.0 mils/coat
Pot Life:	1-2 hours @ 77°F	Dry Film Thickness:	1.4-2.3 mils/coat
Mix Ratio: (by Volume)	2:1	Dry to Recoat:	4-6 hours
Mixing Time:	3-5 minutes	Dry Hard	48 hours
Induction Time:	None	Full Cure:	5 days
VOC (theoretical):	Zero		
Flash Point:	≥ 330°F		24 oz size covers 80 sq ft in one coat (2 coats recommended)
Shelf Life:	6 months in unopened container at 77°F.		96 oz size covers 300 sq ft in one coat (2 coats recommended)
Storage:	Store at 50-77°F in a dry place out of direct sunlight		Note: Drying times are at 70°F and 58% RH. Cool temperatures, high humidity, poor ventilation or heavy film thicknesses will extend dry times. Warmer temperatures and lower humidity will decrease dry times.

FOR PROFESSIONAL USE ONLY

Notes:

Mix Part A thoroughly then add the full contents of Part B to Part A and blend completely (3-5 minutes). A drill mounted impeller is recommended for best mixing. Do not add water to individual components. Apply when air and surface temperatures are 50-90°F and the relative humidity is less than 85%. Do not apply if rain is expected within 48 hours of application. Do not exceed spreading rate as this may cause pinholes, micro-blistering, or a milky appearance. If over 12 hours lapses between coats, lightly scuff sand the surface and remove all dust before applying the next coat.

Also Available: Special colors. Contact us for details.

The information and data given herein are based upon tests and reports considered reliable and believed to be accurate. However, due to circumstances beyond our control including but not limited to surface preparation, application technique, substrate and curing conditions, no guarantee of duplicate performance, expressed or implied, is made.