

Interior/Exterior

**Tintable Dry Erase Basecoat**

**196-4525**

3/15

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A quick dry, waterborne acrylic, high hiding basecoat for use under Dutch Standard Waterborne Dry Erase Coating.</li> <li>• Provides a high hiding, uniform basecoat that can be tinted to a wide variety of colors. The outstanding hiding properties help mask previous coatings and color variations.</li> <li>• Exhibits good holdout and minimal grain raising properties.</li> <li>• Soap and water cleanup.</li> <li>• Very low odor and low VOC. Meets LADCO and OTC regulations.</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• May be applied on interior or exterior, bare or previously coated drywall, plaster, wood, masonry, aluminum, galvanized metal and primed ferrous metal surfaces.</li> <li>• Excellent adhesion over a variety of substrates including previous paint, chalkboards, glass, aluminum, vinyl, galvanized metal and many other clean, sound, substrates.</li> </ul>
<b>COLORS</b> 196-4525 White (Tintable) <b>196-4526 Deep Tint Base</b>	<b>FINISH</b> Flat <b>VEHICLE</b> Waterborne Acrylic <b>FORMULATION</b> Formulated without lead, chrome or mercury

### PHYSICAL DATA

<b>GLOSS RATING</b> Less than 5%	<b>VISCOSITY</b> 96-100 KU
<b>PERCENT SOLIDS</b> Weight: 53% +/- 2.0 Volume: 34% +/- 2.0	<b>NET WT. PER GAL.</b> 11.6 +/- 0.25 lbs./gal.
<b>VOC CATEGORY</b> Less than 150 grams/liter	<b>FLASH POINT</b> Higher than 200°F

### SURFACE PREPARATION & APPLICATION INSTRUCTIONS

<ul style="list-style-type: none"> <li>• Read label directions for detailed instructions. Correct for the cause of any previous paint failures before applying this product.</li> <li>• New plaster and masonry should cure 28 days before applying Dry Erase Basecoat.</li> <li>• Spackling, caulk, patching and taping compounds must be completely dry before applying Dry Erase Basecoat.</li> <li>• A stain blocking primer/sealer is recommended on woods containing bleeding extractives (tannins) and over most stains other than smoke damage from fires and asphalt.</li> <li>• Although this product exhibits excellent adhesion to many surfaces, scuff sanding smooth, hard, and/or glossy surfaces is recommended to optimize adhesion.</li> <li>• Note: This product will continue to cure, harden, and gain adhesion for up to 30 days after application under good conditions.</li> </ul>
--

<b>RECOMMENDED PRIMERS</b> Drywall/Plaster: None Masonry: None Wood: None or 248-88 Versa-Seal Acrylic Stain Block Ferrous Metal: 622-71, 72, 73 Defi-Rust Acrylic Metal Primer Galvanized: None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
---	---

<b>APPLICATION TEMP.</b> Minimum: 50°F Maximum: 90°F	<b>STORAGE TEMP.</b> Minimum: 50°F Maximum: 90°F
--	--

<b>TINTING</b> Up to 4 fluid ounces per gallon with approved colorants. The addition of colorant may extend drying times.	<b>DRYING TIME (Good Conditions)</b> Tack Free: 30 min. To Topcoat: 1 hr. Hard: 18-24 hrs.
---	---

<b>PRACTICAL COVERAGE</b> 300-400 sq. ft. per gallon (Depends on substrate texture and porosity)	<b>REDUCTION</b> Apply without thinning (Use small amounts of clean water only if necessary).
--	---

<b>RECOMMENDED FILM PER COAT</b> Wet: 4.0-5.3 mils Dry: 1.4-1.8 mils	<b>CLEANUP</b> Soap and water
--	-------------------------------

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b> 196-4525 White (Tintable)	1 Gallon 1 Quart
<b>PACKAGING</b> 196-4526 Deep Tint Base	1 Gallon 1 Quart

<b>FREIGHT CLASS</b> Not Regulated	<b>MSDS</b> Available upon request
------------------------------------	------------------------------------

