



TECHNICAL DATA SHEET

Interior

VERSA-SEAL LATEX WALLPAPER UNDERCOATER

244-66

08/13/2001L

Formerly 240

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> • A white latex undercoater suitable for priming most interior surfaces to be wallcovered. Can be used over existing oil or latex paints. • Exceptional adhesion. Fast Dry. • Makes movement easy during paper hanging. Allows for easy removal of wallcoverings. • Soap & water cleanup 	RECOMMENDED USES <ul style="list-style-type: none"> • For use on interior painted and unpainted plaster, drywall, paneling and primed metal surfaces. • Not intended to be used as a finish coat. • Do not mix with oil colors, other paints, or solvents. 						
COLORS 244-66 White	<table border="0"> <tr> <td>FINISH</td> <td>Flat</td> </tr> <tr> <td>VEHICLE</td> <td>Acrylic Emulsion</td> </tr> <tr> <td>FORMULATION</td> <td>Lead, chromate, and mercury free</td> </tr> </table>	FINISH	Flat	VEHICLE	Acrylic Emulsion	FORMULATION	Lead, chromate, and mercury free
FINISH	Flat						
VEHICLE	Acrylic Emulsion						
FORMULATION	Lead, chromate, and mercury free						

PHYSICAL DATA

GLOSS RATING	Flat	VISCOSITY	90-95
PERCENT SOLIDS	By weight: 50.7 ± 2.0% By volume: 38.3 ± 2.0%	NET WT. PER GAL.	11.4 ± 0.25 lbs./gal.
VOC CATEGORY	2.9 lbs./gal. (350 grams/liter)	FLASH POINT	138 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New plaster surfaces should age 30 days before being painted.
- All repairs, patching, and sanding should be done before primer is applied. Existing Wallcovering that is in good condition and adhering to the surface can be primed with this product and subsequently wallcovered.
- Metal surfaces must be primed with the recommended primer then coated with this product before paper is applied. This product can be covered with paper in 2 hours under normal drying conditions. One coat of this product is usually sufficient on most surfaces.

RECOMMENDED PRIMERS Metal 622-72 Defi-Rust Acrylic Metal Primer Galvanizing 245-88 Classic Versa-Seal	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING May be tinted with approved colorants up to 4 oz. per gallon.	DRYING TIME (Good Conditions) Tack free: 1 hrs. To recoat: 2 hrs. Hard: 24 hrs.
PRACTICAL COVERAGE 400 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION Not normally recommended. If necessary use small amounts of clean water. (For spray reduction see recommended application)
RECOMMENDED FILM PER COAT Wet: 3.0-4.0 mils Dry: 1.0-1.5 mils	CLEAN-UP Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	244-66	5 Gallon	Gallon
FREIGHT CLASS	Non-Flammable Paint		MSDS Available upon request.

HPF-0054, Rev. 1, 8/21/98

A division of the Harrison Paint Co. • P.O. Box 8470 Canton, OH 44711
 Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750