



TECHNICAL DATA SHEET

Exterior

VERSA-SEAL EXTERIOR ALKYD WOOD PRIMER

251-77

08/13/2001N

Formerly 95

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> • A white, breathable, oil house paint primer. Can be top-coated with oil or latex based paints. • Seals out many types of stains, including tannins in redwood and cedar. • Dirt and mildew resistant. Blister resistant. • Alkyd formulation is ideal for use when changing from oil to latex based house paints. 	RECOMMENDED USES <ul style="list-style-type: none"> • Recommended as a primer/sealer for use on exterior painted and unpainted wood siding & trim. • Ideal primer for exterior alkyd paints. Can also be used under Wonder Flow House Paint if an alkyd primer is desired. • Do not mix with water or other paint products. • Not intended to be used as a finish coat.
COLORS 251-77 White 251-94 DTB	FINISH Flat VEHICLE Alkyd Oil FORMULATION Lead, chromate, and mercury free

PHYSICAL DATA

GLOSS RATING Flat	VISCOSITY 82-85 K.U.
PERCENT SOLIDS By weight: 76.0 ± 2.0% By volume: 57.1 ± 2.0%	NET WT. PER GAL. 11.7 ± 0.25 lbs./gal.
VOC CATEGORY 2.9 lbs./gal. (350 grams/liter)	FLASH POINT 113 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- Do not paint on surfaces hot from direct sunlight.
- All repairs, patching, and sanding should be done before primer is applied. Glossy surfaces should be lightly sanded to ensure maximum adhesion.
- This product can be top-coated after 12 hours under normal drying conditions. One coat of this product is usually sufficient on most surfaces.

RECOMMENDED PRIMERS None	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING White may be tinted to pastel shades with approved colorants up to 4oz. per gallon. DTB may be tinted to darker shades up to 8oz. per gallon.	DRYING TIME (Good Conditions) Tack free: 12 hrs. To recoat: 24 hrs. Hard: 48 hrs.
PRACTICAL COVERAGE 350-400 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION As supplied (For spray reduction see recommended application)
RECOMMENDED FILM PER COAT Wet: 3.0-4.0 mils Dry: 1.7-2.3 mils	CLEAN-UP Clean up with mineral spirits

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	251-77 251-94	5 Gallon Gallon Quart	Gallon Gallon Quart
FREIGHT CLASS	Flammable Paint	MSDS	Available upon request.

HPF-0054, Rev. 1, 8/21/98