



TECHNICAL DATA SHEET

PRO-STANDARD 2000

Exterior

EXTERIOR LATEX SEMI-GLOSS

326-01

08/14/2001C

Formerly 3003

PRODUCT CHARACTERISTICS

DESCRIPTION	RECOMMENDED USES
<ul style="list-style-type: none"> A professional quality non-chalking latex semi-gloss house & trim paint. Dirt and Mildew resistant. Low VOC & fast dry. Soap & water cleanup. 	<ul style="list-style-type: none"> Recommended for wood siding, trim, shakes, shingles, unglazed brick, stucco, cement, cinder block, and aluminum & vinyl siding. Do not mix with oil colors, other paints or solvents.
COLORS	FINISH
326-01 White 326-92 LTB 326-93 MTB	Semi-Gloss
	VEHICLE
	Vinyl Acrylic Resin
	FORMULATION
	Lead, chromate, and mercury free

PHYSICAL DATA

GLOSS RATING	55-70 %	VISCOSITY	96-100 K.U.
PERCENT SOLIDS	By weight: 44.5 ± 2.0% By volume: 32.6 ± 2.0%	NET WT. PER GAL.	10.2 ± 0.25 lbs./gal.
VOC CATEGORY	3.2 lbs./gal. (380 grams/liter)	FLASH POINT	161 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New stucco or masonry surfaces should age 30 days before being painted. Excessive chalk on previously painted masonry surfaces should be cleaned and treated with Wonder Flow Masonry Sealer/Conditioner.
- New unpainted surfaces should receive one coat of the recommended primer before being painted, especially over redwood or cedar which contain bleeding oils. In all cases, bare metal must be primed. Glossy surfaces should be lightly sanded and primed. Two coats of this product are recommended on most surfaces.
- Previously painted surfaces should be cleaned, patched, and spot-primed as needed then top-coated as indicated for unpainted surfaces. Weathered surfaces in poor condition require the removal of old paint and a prime coat.

RECOMMENDED PRIMERS	RECOMMENDED APPLICATION
Wood 350-77 Exterior Latex Primer Masonry Direct Application Metal 622-72 Defi-Rust Acrylic Metal Primer Galvanizing 245-88 Classic Versa-Seal Aluminum & Vinyl Direct Application	Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
APPLICATION TEMPERATURE Minimum: 38 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING Hundreds of additional colors may be obtained by using the tint bases and approved colorants.	DRYING TIME Tack free: 4 hrs. (Good Conditions) To recoat: 4-6 hrs. Hard: 48 hrs.
PRACTICAL COVERAGE 300-400 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION Not normally recommended. If necessary use small amounts of clean water. (For spray reduction see recommended application)
RECOMMENDED FILM PER COAT	CLEAN-UP
Wet: 4.0-4.5 mils Dry: 1.0-1.5 mils	Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	326-01, 326-92, 326-93	5 Gallon Gallon
FREIGHT CLASS	Non-Flammable Paint	
MSDS	Available upon request.	

HPF-0054, Rev. 1, 8/21/98

A division of the Harrison Paint Co. • P.O. Box 8470 Canton, OH 44711
Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750