



# TECHNICAL DATA SHEET

## PRO-STANDARD 2000

Interior/Exterior

EGGSHELL FILL & FINISH

386-01

08/14/2001A

Formerly 3004

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A professional quality coating designed to fill, seal, and decorate concrete block in one application.</li> <li>• Saves time, labor, and material.</li> <li>• Low VOC.</li> <li>• Soap &amp; water cleanup.</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• Recommended for new unpainted interior or exterior concrete block.</li> <li>• Not recommended for use on tub or shower stalls, floors or any surface that will be under water.</li> <li>• Do not mix with oil colors, other paints, or solvents.</li> </ul>						
<b>COLORS</b> 300-01 White	<table border="0"> <tr> <td><b>FINISH</b></td> <td>Eggshell</td> </tr> <tr> <td><b>VEHICLE</b></td> <td>Latex Emulsion</td> </tr> <tr> <td><b>FORMULATION</b></td> <td>Lead, chromate, and mercury free</td> </tr> </table>	<b>FINISH</b>	Eggshell	<b>VEHICLE</b>	Latex Emulsion	<b>FORMULATION</b>	Lead, chromate, and mercury free
<b>FINISH</b>	Eggshell						
<b>VEHICLE</b>	Latex Emulsion						
<b>FORMULATION</b>	Lead, chromate, and mercury free						

### PHYSICAL DATA

<b>GLOSS RATING</b>	35-40 %	<b>VISCOSITY</b>	115-120 K.U.
<b>PERCENT SOLIDS</b>	By weight: 57.3 ± 2.0% By volume: 45.9 ± 2.0%	<b>NET WT. PER GAL.</b>	10.6 ± 0.25 lbs./gal.
<b>VOC CATEGORY</b>	3.2 lbs./gal. (380 grams/liter)	<b>FLASH POINT</b>	142 ° F Closed Cup

### SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New cement surfaces should age at least 30 days before being painted.
- This product should be applied to new block without a primer. Film thickness can be built up to fill voids. If desired, this product may be re-coated with latex paints after 24 hours under good drying conditions.
- Do not apply to block walls that show signs of water seepage.

<b>RECOMMENDED PRIMERS</b> None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: Not recommended Airless: As supplied with 2000 psi pressure & 0.021 mi. tip
<b>APPLICATION TEMPERATURE</b> Minimum: 50 °F. Maximum: 90 °F.	<b>STORAGE TEMPERATURE</b> Minimum: 35 °F. Maximum: 120 °F.
<b>TINTING</b> Not Recommended	<b>DRYING TIME (Good Conditions)</b> Tack free: 6 hrs. To recoat: 24 hrs. Hard: 7 days
<b>PRACTICAL COVERAGE</b> 100-150 sq. ft./gal. (Depending upon the porosity of the substrate)	<b>REDUCTION</b> Not normally recommended. If necessary use small amounts of clean water.
<b>RECOMMENDED FILM PER COAT</b> Wet: 10.0-15.0 mils Dry: 4.5-6.0 mils	<b>CLEAN-UP</b> Clean up with soap and water

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b>	Special Order Only
<b>FREIGHT CLASS</b>	Non-Flammable Paint
<b>MSDS</b>	Available upon request.

HPF-0054, Rev. 1, 8/21/98