



TECHNICAL DATA SHEET

PRO-STANDARD 4000

Interior/Exterior

LATEX BLOCK FILLER

560-88

08/13/2001C

Formerly 3013

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> • A professional quality coating designed to fill and seal interior or exterior concrete block prior to being top-coated with latex or oil base paints. • Enhances final appearance of finish coat. • Low VOC & fast dry. • Soap & water cleanup. 	RECOMMENDED USES <ul style="list-style-type: none"> • Recommended for new unpainted interior or exterior concrete block. • This product is not intended to be used as a finish coat and must be top-coated with an appropriate interior or exterior paint. • Do not mix with oil colors, other paints, or solvents. 						
COLORS 560-88 White	<table border="0"> <tr> <td>FINISH</td> <td>Flat</td> </tr> <tr> <td>VEHICLE</td> <td>Latex Emulsion</td> </tr> <tr> <td>FORMULATION</td> <td>Lead, chromate, and mercury free</td> </tr> </table>	FINISH	Flat	VEHICLE	Latex Emulsion	FORMULATION	Lead, chromate, and mercury free
FINISH	Flat						
VEHICLE	Latex Emulsion						
FORMULATION	Lead, chromate, and mercury free						

PHYSICAL DATA

GLOSS RATING	Flat	VISCOSITY	135-140 K.U.
PERCENT SOLIDS	By weight: 67.0 ± 2.0% By volume: 46.4 ± 2.0%	NET WT. PER GAL.	13.5 ± 0.25 lbs./gal.
VOC CATEGORY	2.1 lbs./gal. (250 grams/liter)	FLASH POINT	142 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New cement surfaces should age at least 30 days before being painted.
- This product should be applied to new block without a primer. Film thickness can be built up to fill voids. This product may be re-coated with latex or oil base paints after 12 hours under good drying conditions.
- Do not apply to block walls that show signs of water seepage.

RECOMMENDED PRIMERS None	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING May be tinted to light pastel shades with approved colorants not to exceed 2 oz. per gallon.	DRYING TIME (Good Conditions) Tack free: 4 hrs. To recoat: 12 hrs. Hard: 48 hrs.
PRACTICAL COVERAGE 70-100 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION Not normally recommended. If necessary use small amounts of clean water.
RECOMMENDED FILM PER COAT Wet: 16.0-20.0 mils Dry: 8.0-10.0 mils	CLEAN-UP Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING 560-88	5 Gallon Gallon
FREIGHT CLASS Non-Flammable Paint	MSDS Available upon request.

HPF-0054, Rev. 1, 8/21/98