



# TECHNICAL DATA SHEET

## PRO-STANDARD 4000

Interior

LATEX FLAT DRYFALL

590-01

08/14/2001A

Formerly 3014

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>An economical coating designed for spray only application on interior surfaces in commercial and industrial settings.</li> <li>Excellent one-coat hiding properties.</li> <li>"Dry Fall" properties allow for easy cleanup of overspray.</li> <li>Low VOC &amp; fast dry.</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>Recommended for spray application to walls and ceilings of factories, warehouses, garages, barns, and other commercial and industrial building interiors.</li> <li>Do not mix with oil colors, other paints, or solvents.</li> </ul>
<b>COLORS</b> 590-01 White	<b>FINISH</b> Flat  <b>VEHICLE</b> Latex Emulsion  <b>FORMULATION</b> Lead, chromate, and mercury free

### PHYSICAL DATA

<b>GLOSS RATING</b> Flat	<b>VISCOSITY</b> 95-100 K.U.
<b>PERCENT SOLIDS</b> By weight: 49.5 ± 2.0% By volume: 30.6 ± 2.0%	<b>NET WT. PER GAL.</b> 11.4 ± 0.25 lbs./gal.
<b>VOC CATEGORY</b> 3.3 lbs./gal. (400 grams/liter)	<b>FLASH POINT</b> 141 ° F Closed Cup

### SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New plaster or cement surfaces should age at least 30 days before being painted. Glossy surfaces should be lightly sanded before coating.
- This coating should be applied by spray only. Most surfaces require no primer. In cases of extreme porosity such as new concrete block, 342-66 Interior Latex PVA sealer should be used as a prime coat.
- Temperature and Humidity will affect Dryfall characteristics.

<b>RECOMMENDED PRIMERS</b> Porous Surfaces 342-66 Interior Latex PVA Sealer	<b>RECOMMENDED APPLICATION</b> Brush: Not recommended Roller: Not Recommended Spray: Up to 5:1 reduction with clean water Airless: As supplied
<b>APPLICATION TEMPERATURE</b> Minimum: 50 °F. Maximum: 90 °F.	<b>STORAGE TEMPERATURE</b> Minimum: 35 °F. Maximum: 120 °F.
<b>TINTING</b> May be tinted to pastel shades with approved colorants up to 4 oz. per gallon. Tinting may affect Dryfall characteristics.	<b>DRYING TIME (Good Conditions)</b> Tack free: 30 min. To recoat: 45 min. Hard: 24 hrs.
<b>PRACTICAL COVERAGE</b> 200 sq. ft./gal. (Depending upon the porosity of the substrate)	<b>REDUCTION</b> May be reduced up to 5:1 with clean water for conventional spray application.
<b>RECOMMENDED FILM PER COAT</b> Wet: 4.5-6.0 mils Dry: 1.5-2.0 mils	<b>CLEAN-UP</b> Clean up with soap and water

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b>	590-01	5 Gallon
<b>FREIGHT CLASS</b>	Non-Flammable Paint	<b>MSDS</b> Available upon request.

HPF-0054, Rev. 1, 8/21/98

A division of the Harrison Paint Co. • P.O. Box 8470 Canton, OH 44711  
 Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750