



TECHNICAL DATA SHEET

PRO-STANDARD 4000

Interior

LATEX SATIN DRYFALL

592-01

08/14/2001A

Formerly 3015

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none">An economical coating designed for spray only application on interior surfaces in commercial and industrial settings.Excellent one-coat hiding properties."Dry Fall" properties allow for easy cleanup of overspray.Low VOC & fast dry.	RECOMMENDED USES <ul style="list-style-type: none">Recommended for spray application to walls and ceilings of factories, warehouses, garages, barns, and other commercial and industrial building interiors.Do not mix with oil colors, other paints, or solvents.
COLORS 592-01 White	FINISH Satin VEHICLE Latex Emulsion FORMULATION Lead, chromate, and mercury free

PHYSICAL DATA

GLOSS RATING 15-25%	VISCOSITY 90-100 K.U.
PERCENT SOLIDS By weight: 35.0 ± 2.0% By volume: 24.0 ± 2.0%	NET WT. PER GAL. 9.5 ± 0.25 lbs./gal.
VOC CATEGORY 3.3 lbs./gal. (400 grams/liter)	FLASH POINT 151 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- New plaster or cement surfaces should age at least 30 days before being painted. Glossy surfaces should be lightly sanded before coating.
- This coating should be applied by spray only. Most surfaces require no primer. In cases of extreme porosity such as new concrete block, 342-66 Interior Latex PVA sealer should be used as a prime coat.
- Temperature and Humidity will affect Dryfall characteristics.

RECOMMENDED PRIMERS Porous Surfaces 342-66 Interior Latex PVA Sealer	RECOMMENDED APPLICATION Brush: Not recommended Roller: Not Recommended Spray: Up to 5:1 reduction with clean water Airless: As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.	STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.
TINTING May be tinted to pastel shades with approved colorants up to 4 oz. per gallon. Tinting may affect Dryfall characteristics.	DRYING TIME (Good Conditions) Tack free: 30 min. To recoat: 1 hrs. Hard: 24 hrs.
PRACTICAL COVERAGE 200-250 sq. ft./gal. (Depending upon the porosity of the substrate)	REDUCTION May be reduced up to 5:1 with clean water for conventional spray application.
RECOMMENDED FILM PER COAT Wet: 4.5-6.0 mils Dry: 1.5-2.0 mils	CLEAN-UP Clean up with soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING 592-01	5 Gallon
FREIGHT CLASS Non-Flammable Paint	MSDS Available upon request.

HPF-0054, Rev. 1, 8/21/98