



TECHNICAL DATA SHEET

Exterior

COUNTRY ESTATE LINSEED OIL BARN & ROOF PAINT

703-01

6/28/2010

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> An alkyd modified linseed oil paint designed to protect and beautify wood and metal surfaces Flexible and breathable to resist blistering and peeling Dried film is corrosion and mildew resistance High solids / low VOC formulation (compliant for most areas) 	RECOMMENDED USES <ul style="list-style-type: none"> Ideal for use on wood or metal barns, roofs, silos, sheds, fences and many other surfaces Great for properly prepared new or old wood or for recoating Not for use on horizontal surfaces where water collects (roofs must be pitched) Do not apply over asphalt or tar products
COLORS 703-01 White 703-02 Black 703-32 Red 703-49 Hunter Green	FINISH Low Lustre VEHICLE Alkyd modified linseed oil FORMULATION Formulated without lead, chrome and mercury

PHYSICAL DATA (Mixed Components)

GLOSS RATING Low Lustre PERCENT SOLIDS Weight: 91% ± 2.0 Volume: 81% ± 2.0 VOC CATEGORY Less than 150 grams/liter	VISCOSITY 76-80 KU NET WT/GAL 13.8 ± 0.25 lbs./gal. FLASH POINT 115°F (Setaflash)
--	--

SURFACE PREPARATION & APPLICATION INSTRUCTIONS

- Read label directions for detailed instructions.
- Correct for the cause of any previous paint failures before applying this product.
- Apply a coat of Defi-Rust Oil Base Metal Primer if additional corrosion resistance on bare metal is desired (follow label instructions).

RECOMMENDED PRIMERS Wood Direct application Metal 611-XX Defi-Rust Oil Base Metal Primers Galvanizing 611-88 Defi-Rust Galvanized Metal Primer	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
APPLICATION TEMP. Minimum: 50°F Maximum: 90°F	STORAGE TEMP. Minimum: 50°F Maximum: 90°F
TINTING Not to be tinted	DRYING TIME (Good Conditions) Tack Free: 12-16 hrs. To Recoat: 18-24 hrs. Hard: 5-7 days
PRACTICAL COVERAGE 400 sq. ft./gal. (250-300 on very porous wood) (Depends on substrate texture and porosity)	REDUCTION Apply without thinning
RECOMMENDED FILM PER COAT Wet: 3.8-4.2 mils Dry: 3.0-3.4 mils	CLEANUP Mineral spirits

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	703-01 703-02 703-32 703-49	5 Gallon 1 Gallon Kit
FREIGHT CLASS Combustible Paint	MSDS Available upon request	

A division of the Harrison Paint Co. • 1329 Harrison Ave SW, Canton, OH 44706
 Phone: (330) 455-5125 • Customer Service: 1-800-321-0680 • Fax: (330) 454-1750