

Interior/Exterior

## RUBBER BASE SWIMMING POOL PAINT

707-01

3/22/2010

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A solventborne coating designed to protect and beautify concrete, masonry, gunite, and other masonry surfaces</li> <li>• Outstanding performance against mild acids, alkalis, and other pool chemicals in fresh or salt water</li> <li>• Dried film resists weather, UV degradation, algae, and mildew</li> <li>• Low VOC formulation (compliant for most areas)</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• Ideal for use on residential and commercial swimming pools, non-potable fountains and other masonry surfaces</li> <li>• May be applied to bare masonry or over previous rubber base pool paints</li> <li>• Not for use on metal, fiberglass, or vinyl lined pools</li> <li>• Do not use over epoxy, urethane, or other impervious coatings</li> </ul>
<b>COLORS</b> 707-01 White 707-02 Black 707-30 Aquamarine 707-31 Ocean Blue	<b>FINISH</b> Flat  <b>VEHICLE</b> Styrene-Butadiene Copolymer Resin  <b>FORMULATION</b> Formulated without lead, chrome and mercury

### PHYSICAL DATA

<b>GLOSS RATING</b> <5% <b>PERCENT SOLIDS</b> Weight: 62% ± 2.0 Volume: 44% ± 2.0 <b>VOC CATEGORY</b> Less than 340 grams/liter	<b>VISCOSITY</b> 80-84 KU <b>NET WT/GAL</b> 13.6 ± 0.25 lbs./gal. <b>FLASH POINT</b> 107°F (Setaflash)
---	--

### SURFACE PREPARATION & APPLICATION INSTRUCTIONS

<ul style="list-style-type: none"> <li>• Read label directions for detailed instructions.</li> <li>• Correct for the cause of any previous paint failures before applying this product.</li> <li>• New masonry should age at least 60 days before being painted.</li> <li>• Allow pool to dry for 7 days after draining before surface preparation.</li> <li>• Allow paint to cure for 7 days before filling pool with water.</li> <li>• CAUTION: Surface contaminations such as oil, grease, suntan lotion, water as well as other materials, may cause a hazardous slippery surface requiring caution in preventing injury.</li> </ul>
--

<b>RECOMMENDED PRIMERS</b> None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
<b>APPLICATION TEMP.</b> Minimum: 50°F Maximum: 90°F	<b>STORAGE TEMP.</b> Minimum: 50°F Maximum: 90°F
<b>TINTING</b> Not to be tinted	<b>DRYING TIME (Good Conditions)</b> Tack Free: 1 hr. To Recoat: 18 hrs. Hard: 5-7 days
<b>PRACTICAL COVERAGE</b> 350-400 sq. ft./gal. (Depends on substrate texture and porosity)	<b>REDUCTION</b> Apply without thinning
<b>RECOMMENDED FILM PER COAT</b> Wet: 4.0-4.6 mils Dry: 1.8-2.0 mils	<b>CLEANUP</b> Aromatic 100 or Xylene

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b> 707-01 707-02, 707-30, 707-31	5 Gallon 1 Gallon 1 Gallon
<b>FREIGHT CLASS</b> Combustible Paint	<b>MSDS</b> Available upon request