

Interior/Exterior

Dura-Gard Acrylic Latex Tred-Safe

730-99

8/3/17

PRODUCT CHARACTERISTICS

DESCRIPTION			RECOMMENDED USES		
<ul style="list-style-type: none"> A waterborne anti-slip coating formulated for use on bare or previously painted wood and concrete surfaces and primed metal Designed for light to moderate duty (foot and wheelchair traffic) Provides a tough, coarse film that reduces the chance of slipping (This product does not eliminate the possibility of slipping completely) Soap and water cleanup Low odor and low VOC formulation (compliant for most areas) 			<ul style="list-style-type: none"> Ideal for use on walkways, steps, ramps, boat decks, locker room floors, tennis courts and other interior or exterior applications Surfaces to be coated must be properly prepared This product is not designed for immersion service or for areas where water tends to collect. This product is not designed for use under cars, trucks, tow motors or other vehicular traffic or for heavy-duty applications 		
COLORS			FINISH		
730-99 Tinting White	730-08 Yellow	730-14 Walnut Brown	Flat Grit		
730-02 Black	730-11 Silver Gray	730-15 Bombay	VEHICLE		
730-05 Light Gray	730-12 Red	730-16 Navy Gray	Acrylic Latex		
730-07 Handicap Blue	730-13 Green		FORMULATION		
			Formulated without lead, chrome and mercury		

PHYSICAL DATA

(Physical properties are based on 730-99 Tinting White. Other products in the series will be similar but may not be exactly the same.)

GLOSS RATING	Flat	VISCOSITY	125-130 KU
PERCENT SOLIDS	Weight: 65% ± 2.0	Volume: 47% ± 2.0	NET WT/GAL
VOC CATEGORY	Less than 25 grams/liter		12.5 ± 0.25 lbs./gal.
			FLASH POINT
			>200°F (Setaflash)

SURFACE PREPARATION & APPLICATION INSTRUCTIONS

- Read label directions for detailed instructions and precautions.
- Correct for the cause of any previous paint failures before applying this product.
- New masonry/concrete should age at least 30 days before being painted.
- Bare metal must first be primed with a Defi-Rust Acrylic Metal Primer following label directions before applying this product.

RECOMMENDED PRIMERS		RECOMMENDED APPLICATION	
Wood	Direct Application	Brush:	As supplied
Metal	622-XX Defi-Rust Acrylic Metal Primer	Roller:	As supplied
Galvanizing	622-XX Defi-Rust Acrylic Metal Primer	Spray:	Not recommended
Masonry/Concrete	Direct Application	Trowel:	As supplied
APPLICATION TEMP.	Minimum: 50°F	Maximum: 90°F	STORAGE TEMP.
	Minimum: 50°F	Maximum: 90°F	
TINTING	Tinting White may be tinted with up to 2 fl. oz. of approved colorants.	DRYING TIME	Tack Free: 4-8 hrs.
		(Good Conditions)	Recoat: 18-24 hrs.
			Light Walking: 18-24 hrs
			Hard/Cured: 7-14 days
PRACTICAL COVERAGE	100-125 sq. ft./gal. (Depends on substrate texture and porosity)	REDUCTION	Apply without thinning (Use small amounts of clean water only if necessary)
RECOMMENDED FILM PER COAT	Wet: 12.5-16.0 mils Dry: 6.0-7.5 mils	CLEANUP	Soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	730-99 and all colors	5 Gallon	1 Gallon
FREIGHT CLASS	Not Regulated	MSDS	Available upon request