



# TECHNICAL DATA SHEET

Exterior

## VERSA-LASTIC BOND TITE SEALER

742-77

11/23/2001B

Formerly 1510

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A water based masonry conditioner that aids in the binding of mild chalk found on previously painted masonry surfaces.</li> <li>• Excellent penetrating power.</li> <li>• Ideal for topcoating with Versa-Lastic elastomeric coatings.</li> <li>• May be used under most latex masonry paints.</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• Recommended for use on most exterior masonry surfaces where mild chalk is encountered. Not for use over excessive chalk.</li> <li>• Do not mix with oil colors, other paints, or solvents.</li> <li>• Not intended to be used as a finish coat.</li> </ul>						
<b>COLORS</b> 742-77 White	<table border="0"> <tr> <td><b>FINISH</b></td> <td>Flat</td> </tr> <tr> <td><b>VEHICLE</b></td> <td>Acrylic Resin</td> </tr> <tr> <td><b>FORMULATION</b></td> <td>Lead, chromate, and mercury free</td> </tr> </table>	<b>FINISH</b>	Flat	<b>VEHICLE</b>	Acrylic Resin	<b>FORMULATION</b>	Lead, chromate, and mercury free
<b>FINISH</b>	Flat						
<b>VEHICLE</b>	Acrylic Resin						
<b>FORMULATION</b>	Lead, chromate, and mercury free						

### PHYSICAL DATA

<b>GLOSS RATING</b>	Less Than 5 %	<b>VISCOSITY</b>	72-74 K.U.
<b>PERCENT SOLIDS</b>	By weight: 29.7 ± 2.0% By volume: 22.9 ± 2.0%	<b>NET WT. PER GAL.</b>	9.3 ± 0.25 lbs./gal.
<b>VOC CATEGORY</b>	2.1 lbs./gal. (250 grams/liter)	<b>FLASH POINT</b>	151 ° F Closed Cup

### SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- Make all repairs such as caulking or pointing-up before applying this product.
- Chalky surfaces should be cleaned by wire brushing and/or power washing to remove as much excess chalk as is possible. One coat of this product is usually sufficient to produce a sound surface for topcoating with Wonder Flow Masonry Paint.
- This product can be coated after 4 hours under good drying conditions.

<b>RECOMMENDED PRIMERS</b> None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
<b>APPLICATION TEMPERATURE</b> Minimum: 50 °F. Maximum: 90 °F.	<b>STORAGE TEMPERATURE</b> Minimum: 35 °F. Maximum: 120 °F.
<b>TINTING</b> May be tinted to pastel shades with approved colorants up to 4 oz. per gallon.	<b>DRYING TIME (Good Conditions)</b> Tack free: 2 hrs. To recoat: 4 hrs. Hard: 18 hrs.
<b>PRACTICAL COVERAGE</b> 400-450 sq. ft./gal. (Depending upon the porosity of the substrate)	<b>REDUCTION</b> Not normally recommended. If necessary use small amounts of clean water.
<b>RECOMMENDED FILM PER COAT</b> Wet: 3.5-4.0 mils Dry: 0.8-1.0 mils	<b>CLEAN-UP</b> Clean up with soap and water

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b>	742-77	5 Gallon	Gallon
<b>FREIGHT CLASS</b>	Non-Flammable Paint		<b>MSDS</b> Available upon request.

HPF-0054, Rev. 1, 8/21/98