

## Technical Data Sheet

**Product #:** 819-00 Clear Gloss

**Product Name:** Quick Dry Alkyd Varnish

**Description:** A fast drying, solventborne finish designed to protect and beautify many interior wood surfaces. Resistant to water, mild solvents, weak acid and alkaline materials. May be used over most stains and wood fillers. Ideal for cabinets, doors, handrails, baseboards, crown molding, chair rails, wainscoting, paneling, furniture and other wood substrates.

### Properties:

<b><u>Physical:</u></b>	<b><u>Application:</u></b>
Viscosity (#2 Zahn Cup): 20-30 seconds	Viscosity: As is
Weight/Gallon: 7.0 +/- 0.25 lbs./gal.	Reduction: None required
Gloss: 90% minimum	Reducer: None required
Weight Solids: 34% +/- 2.0	Application Method: Brush & Spray
Volume Solids: 28% +/- 2.0	Clean-Up: VM&P Naphtha or Xylene
VOC (calculated): 550 grams/liter (4.6 lbs./gal.)	Coverage (sq. ft./gallon): 400-500
Flash Point: (Setaflash) 79°F	Wet Film Thickness: 3.2-4.0 mils
Shelf Life: One year minimum in unopened container @ 77°F	Dry Film Thickness: 0.9-1.1 mils
Storage: Store at 60-80°F in a dry place out of direct sunlight	Dry to Handle: 30 minutes
	Dry to Sand/Recoat: 2 hours
	Dry Hard: 18-24 hours
	<small>Note: Drying times are at 77°F and 50% RH. Cool temperatures, high humidity, poor ventilation or heavy film thicknesses will extend dry times.</small>

**Notes:** See label for detailed instructions and warnings. Not designed for exterior wood surfaces. If over 24 hours lapses between coats, lightly scuff sand and clean the surface before applying the next coat.

The information and data given herein are based upon tests and reports considered reliable and believed to be accurate. However, due to circumstances beyond our control including but not limited to surface preparation, application technique, substrate and curing conditions, no guarantee of duplicate performance, expressed or implied, is made.