

TECHNICAL DATA SHEET

Exterior

WOODUCK EXTERIOR SEMI-TRANSPARENT STAIN

832-96

08/14/2001K Formerly 1141

PRODUCT CHARACTERISTICS

DESCRIPTION	RECOMMENDED US	ES	
 A semi-transparent exterior stain for use on both bare and previously stained wood surfaces. Provides a decorative and protective coating without altering the natural texture of the wood or completely obscuring the grain. 	 Recommended for smooth or rough sawn siding, shakes, shingles, plywood, and many other similar wood surfaces. Not for use on decks or other high traffic areas. Do not mix with oil colors, other paints, or solvents. 		
Resists mildew, peeling, blistering, and UV degradation.	Not to be used as a clear coating.		
Soap & water cleanup.			
COLORS	FINISH	Flat	
832-96 CLB	VEHICLE	Acrylic Latex	
	FORMULATION	Lead, chromate, and mercury free	

PHYSICAL DATA

GLOSS RATING	Flat	VISCOSITY	70-74 K.U.
PERCENT SOLIDS	By weight: 44.4 ± 2.0% By volume: 33.4 ± 2.0%	NET WT. PER GAL.	10.0 ± 0.25 lbs./gal.
VOC CATEGORY	2.9 lbs./gal. (350 grams/liter)	FLASH POINT	147 ° F Closed Cup

SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- All surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting.
- No primer is recommended as this will affect the transparency of the stain. One coat of this stain is usually sufficient on most surfaces. Two coats may be applied, but the second coat may hide the wood grain more than desired.
- Previously stained surfaces need only be clean prior to application. Covering a previous color of semi-transparent stain will affect the resulting color appearance. It is recommended that the stain be tested in an inconspicuous area for color determination.

RECOMMENDED PR	RIMERS		RECOMMENDED APPLICATION	
None			Brush:	As supplied
			Roller:	As supplied
			Spray:	As supplied
			Airless:	As supplied
APPLICATION TEMPERATURE Minimum: 50 °F. Maximum: 90 °F.		STORAGE TEMPERATURE Minimum: 35 °F. Maximum: 120 °F.		
TINTING	Hundreds	s of additional colors may be obtained by	DRYING TIME	Tack free: 1 hrs.
	using the	tint bases and approved colorants.	(Good Conditions)	To recoat: 2 hrs.
				Hard: 24 hrs.
PRACTICAL	250-400 s	sq. ft./gal.	REDUCTION	Not normally recommended. If necessary use small
COVERAGE	(Dependi	ng upon the porosity of the substrate)		amounts of clean water.
				(For spray reduction see recommended application)
RECOMMENDED	Wet:	3.0-4.0 mils	CLEAN-UP	Clean up with soap and water
FILM PER COAT	Dry:	1.0-1.2 mils		

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING	All Tint Bases	5 Gallon	Gallon
FREIGHT CLASS	Non-Flammable Paint	MSDS	Available upon request.

HPF-0054, Rev. 1, 8/21/98

A division of the Harrison Paint Co. • P.O. Box 8470 Canton, OH 44711 Phone: (330) 455-5125 Customer Service: 1-800-321-0680 Fax: (330) 454-1750