



TECHNICAL DATA SHEET

Interior/Exterior

2K WATERBORNE EPOXY SWIMMING POOL PAINT

910-01

3/26/2010

PRODUCT CHARACTERISTICS

DESCRIPTION <ul style="list-style-type: none"> • A two-component waterborne coating designed to protect and beautify masonry, metal and fiberglass surfaces • Excellent chemical and corrosion resistance • Dries to a heavy-duty, high gloss film with outstanding resistance to wear, abrasion, algae and mildew • Low VOC formulation (compliant for most areas) 	RECOMMENDED USES <ul style="list-style-type: none"> • Ideal for use on residential and commercial swimming pools • May be applied to bare or previously epoxy coated surfaces • Not for use on vinyl lined pools
COLORS 910-01 White 910-02 Black 910-30 Aquamarine 910-31 Ocean Blue	FINISH High Gloss VEHICLE Polyamine Epoxy FORMULATION Formulated without lead, chrome and mercury

PHYSICAL DATA (Mixed Components)

GLOSS RATING 90%+	VISCOSITY 85-95 KU
PERCENT SOLIDS Weight: 55% ± 2.0 Volume: 43% ± 2.0	NET WT/GAL 10.4 ± 0.25 lbs./gal.
VOC CATEGORY Less than 250 grams/liter	FLASH POINT 130°F (Setaflash)

SURFACE PREPARATION & APPLICATION INSTRUCTIONS

<ul style="list-style-type: none"> • Read label directions and pool paint flyer for detailed instructions. • Correct for the cause of any previous paint failures before applying this product. • New masonry should age at least 60 days before being painted. • Allow pool to dry for 7 days after draining before surface preparation. • Allow coating to cure for 7 days before filling pool with water. • No induction time needed after mixing; pot life is approximately 2 hours. • CAUTION: Surface contaminations such as oil, grease, suntan lotion, water as well as other materials, may cause a hazardous slippery surface requiring caution in preventing injury.
--

RECOMMENDED PRIMERS None	RECOMMENDED APPLICATION Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
APPLICATION TEMP. Minimum: 60°F Maximum: 90°F	STORAGE TEMP. Minimum: 50°F Maximum: 90°F
TINTING Not to be tinted	DRYING TIME (Good Conditions) Tack Free: 4-8 hrs. To Recoat: 8-12 hrs. Hard: 5-7 days
PRACTICAL COVERAGE 350-400 sq. ft./gal. (Depends on substrate texture and porosity)	REDUCTION Apply without thinning (Use small amounts of clean water only if necessary)
RECOMMENDED FILM PER COAT Wet: 4.0-4.6 mils Dry: 1.7-2.0 mils	CLEANUP Soap and water

PACKAGING AND DISTRIBUTION

STANDARD PACKAGING 910-01 910-02 910-30 910-31	1 Gallon Kit
FREIGHT CLASS Combustible Paint	MSDS Available upon request