



# TECHNICAL DATA SHEET

Exterior

## LATEX TRAFFIC ZONE MARKING PAINT

920-01

08/14/2001E

Formerly 331

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>• A latex paint formulated for marking traffic zones of parking lots.</li> <li>• One gallon provides 1,000 feet of four inch line.</li> <li>• White is tintable to light blue for handicap marking.</li> <li>• Soap &amp; water cleanup.</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>• Recommended for marking of parking lots, driveways, walkways, and curbs. of asphalt or concrete.</li> <li>• Do not mix with oil colors, other paints, or solvents.</li> </ul>
<b>COLORS</b> 920-01 White 920-33 Yellow	<b>FINISH</b> Flat  <b>VEHICLE</b> Latex Emulsion  <b>FORMULATION</b> Lead, chromate, and mercury free

### PHYSICAL DATA

<b>GLOSS RATING</b> Flat	<b>VISCOSITY</b> 95-98
<b>PERCENT SOLIDS</b> By weight: 53.3 ± 2.0% By volume: 35.7 ± 2.0%	<b>NET WT. PER GAL.</b> 11.5 ± 0.25 lbs./gal.
<b>VOC CATEGORY</b> 3.8 lbs./gal. (450 grams/liter)	<b>FLASH POINT</b> 142 ° F Closed Cup

### SURFACE PREPERATION & APPLICATION INSTRUCTIONS

- Make sure all surfaces are reasonably clean and free of surface contaminants.
- New concrete should be allowed to cure for 30 days before being painted; asphalt requires 90 days.
- Do not apply if rain is forcasted within 24 hours.
- Surfaces are dry for foot or vehicle traffic after 4 hours under good drying conditions.

<b>RECOMMENDED PRIMERS</b> None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: Up to 10:1 reduction with clean water Airless: As supplied
<b>APPLICATION TEMPERATURE</b> Minimum: 50 °F. Maximum: 90 °F.	<b>STORAGE TEMPERATURE</b> Minimum: 35 °F. Maximum: 120 °F.
<b>TINTING</b> White may be tinted to pastel shades with approved colorants up to 4oz. per gallon.	<b>DRYING TIME (Good Conditions)</b> Tack free: 30 min. To recoat: 2 hrs. Hard: 4 hrs.
<b>PRACTICAL COVERAGE</b> 1,000 ft. of 4 inch line per gal.	<b>REDUCTION</b> Not normally recommended. If necessary use small amounts of clean water. (For spray reduction, see recommended application)
<b>RECOMMENDED FILM PER COAT</b> Wet: 4.8-5.0 mils Dry: 1.7-1.9 mils	<b>CLEAN-UP</b> Clean up with soap and water

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b>	920-01, 920-33	5 Gallon	Gallon
<b>FREIGHT CLASS</b>	Non-Flammable Paint		<b>MSDS</b> Available upon request.

HPF-0054, Rev. 1, 8/21/98