

Interior/Exterior

## 2K POLYAMIDE EPOXY SWIMMING POOL PAINT

909-01

3/26/2010

### PRODUCT CHARACTERISTICS

<b>DESCRIPTION</b> <ul style="list-style-type: none"> <li>A two-component solventborne coating designed to protect and beautify masonry, metal and fiberglass surfaces</li> <li>Excellent chemical and corrosion resistance</li> <li>Dries to a heavy-duty, high gloss film with outstanding resistance to wear, abrasion, algae and mildew</li> <li>Low VOC formulation (compliant for most areas)</li> </ul>	<b>RECOMMENDED USES</b> <ul style="list-style-type: none"> <li>Ideal for use on residential and commercial swimming pools</li> <li>May be applied to bare or previously epoxy coated surfaces</li> <li>Do not use over rubber base or chlorinated rubber coatings</li> <li>Not for use on vinyl lined pools</li> </ul>
<b>COLORS</b> 909-01 White 909-02 Black 909-30 Aquamarine 909-31 Ocean Blue	<b>FINISH</b> High Gloss  <b>VEHICLE</b> Polyamide Epoxy  <b>FORMULATION</b> Formulated without lead, chrome and mercury

### PHYSICAL DATA (Mixed Components)

<b>GLOSS RATING</b> 90%+ <b>PERCENT SOLIDS</b> Weight: 67% ± 2.0 Volume: 50% ± 2.0 <b>VOC CATEGORY</b> Less than 340 grams/liter	<b>VISCOSITY</b> 75-85 KU <b>NET WT/GAL</b> 11.0 ± 0.25 lbs./gal. <b>FLASH POINT</b> 84°F (Setaflash)
--	---

### SURFACE PREPARATION & APPLICATION INSTRUCTIONS

<ul style="list-style-type: none"> <li>Read label directions and pool paint flyer for detailed instructions.</li> <li>Correct for the cause of any previous paint failures before applying this product.</li> <li>New masonry should age at least 60 days before being painted.</li> <li>Allow pool to dry for 7 days after draining before surface preparation.</li> <li>Allow coating to cure for 7 days before filling pool with water.</li> <li>Allow 30 minute induction time after mixing; pot life is approximately 8 hours.</li> <li><b>CAUTION:</b> Surface contaminations such as oil, grease, suntan lotion, water as well as other materials, may cause a hazardous slippery surface requiring caution in preventing injury.</li> </ul>
---

<b>RECOMMENDED PRIMERS</b> None	<b>RECOMMENDED APPLICATION</b> Brush: As supplied Roller: As supplied Spray: As supplied Airless: As supplied
<b>APPLICATION TEMP.</b> Minimum: 50°F Maximum: 90°F	<b>STORAGE TEMP.</b> Minimum: 50°F Maximum: 90°F
<b>TINTING</b> Not to be tinted	<b>DRYING TIME (Good Conditions)</b> Tack Free: 4-8 hrs. To Recoat: 12-18 hrs. Hard: 5-7 days
<b>PRACTICAL COVERAGE</b> 400-500 sq. ft./gal. (Depends on substrate texture and porosity)	<b>REDUCTION</b> Apply without thinning
<b>RECOMMENDED FILM PER COAT</b> Wet: 3.2-4.0 mils Dry: 1.6-2.0 mils	<b>CLEANUP</b> Aromatic 100 or Xylene

### PACKAGING AND DISTRIBUTION

<b>STANDARD PACKAGING</b> 909-01 909-02 909-30 909-31	2 Gallon Kit
<b>FREIGHT CLASS</b> Flammable Paint	<b>MSDS</b> Available upon request